

# TECHNICAL DATA SHEET



## DRIPSTOP C0381 110

PROPERTY	TESTING METHOD	UNIT	VALUE
Composition			PES/PE/synthetic rubber
Treatment			selfadhesive
Special characteristic			water absorption
Weight	EN 29073-1	g/m <sup>2</sup>	±10% 110
Thickness	EN ISO 9073-2	mm	<1
Water absorption 0°	FILC int. 19	g/m <sup>2</sup>	min 1000 <sup>*1</sup>
Water absorption 45°	FILC int. 19	g/m <sup>2</sup>	min 800 <sup>*1</sup>
Water absorption 90°	FILC int. 19	g/m <sup>2</sup>	min 600 <sup>*1</sup>
Water absorption	DIN 53923	g/100cm <sup>2</sup>	0° 45° 90° 11,44 <sup>*1</sup> 10,42 <sup>*1</sup> 9,48 <sup>*1</sup>
Water absorption	NF P 15-203-1	g/m <sup>2</sup>	min 750 <sup>*1</sup>
Flammability	EN 13501-1		A2 - s1, d0 <sup>*1</sup>
Peel adhesion MD	FILC int. 29	N/25mm	min 10 <sup>*1</sup>
Adhesion after ageing - MD	Filc int.22	N/25 mm	improved
Sound absorbtion	EN ISO 354	Hz	125Hz 500Hz 1000Hz 2000Hz 4000Hz 0,02 0,04 0,04 0,12 0,42
Rainfall noise sound insulation	ISO 140-18	dB	L <sub>IA</sub> ΔL <sub>IA</sub> 71 <sup>*2</sup> 69 <sup>*1</sup> 2
Thermal conductivity (λ)	DIN 52612	W/mK	0,038
Bacteria resistance	DIN EN 14119		Index 0 - No visible growth under the microscope - 50x
Colour			white-black melange
Width		mm	max 1500
∅ Card pipe		mm	76

\*1 - Felt on metal sheet

\*2 - Metal sheet

## WORKING CONDITIONS

- DR!PSTOP and the metal sheet should be laminated at a working temperature of +10°C or more. We recommend that coils and anticondensation membrane are stored where the production takes place.
- The surface of the metal sheet where DR!PSTOP will be applied must be dry and free of dust, oils, silicons, rust or anything similar. Dirtiness prevents good contact between the adhesive and the metal sheet, consequently the quality of the end product could suffer.
- DR!PSTOP should also not be applied to surfaces which contain softeners such as Plastisol or similar.
- To obtain a good adhesion it is necessary to ensure equable pressure all over the surface between the metal sheet and DR!PSTOP.
- A metal roof with DR!PSTOP membrane should be built according to current building standards and standard building practices.
- Prevention of capillarity rise should be carried out. In order to allow DR!PSTOP to get dry, sufficient ventilation has to be provided.

## STORAGE

DR!PSTOP should be stored in a dry, closed space at the temperature between +5°C ~ +30°C. It should not be exposed to direct sunlight. If stored according to the given conditions, the quality of material will not change in a period of one year.

## WARNING

- The bonding is permanent. If removed, DR!PSTOP can not be glued again to the surface.
- Do not expose DR!PSTOP side of roof panel to direct sunlight.
- In case of contamination of DR!PSTOP, we recommend to clean the material with water.

## OTHER

- Applied on a profiled metal sheet DR!PSTOP resists environmental temperatures from -40°C to +80°C.
- For further information please contact Filc d.d.
- The given values correspond to the average of laboratory results and to our present level of technical knowledge and experience. The user should test for himself whether the product and the application are suited for his purposes. Possible patent rights, existing laws and regulations must be observed by the user as his own responsibility. Due to our continuing product development the information in this Technical Data can change without prior notice.

